ARclad® IS-8901 Double-Coated Film Bonding Tape



PRODUCT DESCRIPTION

ARclad® IS-8901 is a thick double-coated acrylic adhesive on a black polyester film, ideal for rough surfaces where gap filling is required.

FEATURES

- Heavy adhesive mass
- High tack acrylic pressure-sensitive adhesive
- Black polyester carrier film
- Selfwound paper release liner
- Good adhesion to low energy surfaces

BENEFITS


- Excellent bond strength to foams, rubbers, most plastics, metals and low surface energy substrates
- Conformable and gap filling
- Easy to die cut and apply

PRODUCT APPLICATIONS

Suggested nameplate, mobile phone lens, display and other assembly applications where immediate adhesion on a great variety of surfaces is required. Users should test the product to ensure it meets the specific needs of their application(s). Adhesives Research can tailor the product to meet the needs of specific applications as requested by customers.

PRODUCT PROFILE AND DIAGRAM

Adhesive	Carrier	Adhesive	D/F K-60 Paper Liner
3.5 mil (89 um)	1 mil (25 um) Black PET	3.5 mil (89 um)	3.2 mil (81 um)



Reference Test Methods: PSTC-133, ASTM D-1000

ADHESIVE PROPERTIES

180° Peel Adhesion (12" min.) 5 min. Dwell 23 hr. Dwell

Test Methods

PSTC-101, ASTM D-3330, ART #1005 PSTC-101, ASTM D-3330, ART #1024

Typical Values

SS – 50 oz./in. SS – 70 oz./in.

ARclad® IS-8901 Double-Coated Film Bonding Tape



STATIC SHEAR

Temperature Area Load Minutes to Failure 72°F ½" x ½" 500 g. 60

Reference Test Methods: PSTC-107, ART #1011

STORAGE AND SHELF LIFE

One year from date of manufacturing when stored at 70°F (21°C), 50% R.H.

SERVICE TEMPERATURE RANGES

Minimum Application Temperature: 50°F (10°C)
Maximum Operating Temperature: 250°F (121°C)

(Revision - 11/04/09)

APPLICATION AND STORAGE OF PRESSURE-SENSITIVE ADHESIVE TAPES

Pressure-sensitive adhesive tapes function as a mechanical product; however, the adhesive itself is a chemical composition that can be sensitive to environmental conditions. A purchaser of pressure-sensitive adhesive products should be aware of the shelf life of each product and not purchase more than it can use before the expiration date. Shipping and storage conditions affect shelf life. The optimum storage temperature is 70°F (21°C). Cool, dry storage is recommended.

For best results...

- The surfaces you wish to bond should be clean and free of oil, moisture and dust. If the surface temperature is below 40°F, it may be difficult to achieve a proper bond.
 Do not use a pressure-sensitive adhesive product where it will be exposed to temperatures lower or higher than those
- 2) Do not use a pressure-sensitive adhesive product where it will be exposed to temperatures lower or higher than those designated for each product. Heat can destroy the effectiveness of the bond and extreme cold can cause the adhesive to harden and not adhere properly.
- 3) When the tape is applied, use firm hand or lamination pressure to achieve contact between the adhesive and the surface to which it is applied. Hand rollers or nip rollers may be needed for certain products or applications.

Consult your Adhesives Research sales representative if you need additional information.

WARRANTY AND DISCLAIMER

AR expressly warrants to Purchaser that its product, under normal and intended use, maintenance and storage, is free from defects in workmanship for twelve (12) months from the date of manufacturer, unless otherwise stated. THIS WARRANTY IS GIVEN IN LIEU OF ALL OTHER WARRANTIES. AR MAKES NO WARRANTY AS TO EXPERIMENTAL AND DEVELOPMENTAL SAMPLES OR MATERIALS. AR MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No provisions, statements, diagrams, drawings or pictures contained in any product literature, price list, catalogue, purchase order, product data sheet, order acknowledgment, invoice, delivery ticket, or any other communication by AR, including information on AR's website or statements made by AR's employees or agents, constitute express warranties. Results of tests and recommendations included in communications of AR do not constitute express warranties. MANY FACTORS MAY AFFECT THE USE AND PERFORMANCE OF AN AR PRODUCT IN A PARTICULAR APPLICATION, INCLUDING, AMONG OTHERS, THE PRODUCT SELECTED FOR USE, THE CONDITIONS IN WHICH THE PRODUCT IS USED, THE TIME AND ENVIRONMENTAL CONDITIONS IN WHICH THE PRODUCT IS EXPECTED TO PERFORM, THE MATERIALS TO BE USED WITH THE PRODUCT; THE SURFACE PREPARATION OF THOSE MATERIALS, AND THE APPLICATION METHOD FOR THE PRODUCT; THEREFORE, PURCHASER ACCEPTS RESPONSIBILITY FOR DETERMINING WHETHER AR'S PRODUCT IS FIT FOR A PARTICULAR PURPOSE AND SUITABLE FOR PURCHASER'S METHOD OF APPLICATION. AR retains the right to modify or change its products if in AR's judgment it is advisable.

Purchaser's exclusive remedy and AR's sole obligation for any breach of warranty is limited to, at AR's option, either: 1) replacement of AR's product, or 2) reimbursement of the purchase price of AR's product. AR DISCLAIMS ANY OTHER OBLIGATION OR LIABILITIES ARISING OUT OF BREACH OF WARRANTY. AR will not be liable of any loss, damage, expense or consequential, incidental or special damages of any kind.

ARclad® is a registered trademark of Adhesives Research, Inc. Adhesives Research® is a registered service mark of Adhesives Research, Inc. for engineering and design services in the field of pressure-sensitive adhesive systems.

©2014 Adhesives Research. Inc. Printed in USA.

Internet: www.adhesivesresearch.com

Adhesives Research, Inc. 400 Seaks Run Road, P.O. Box 100 Glen Rock, PA 17327 Toll-free: 800-445-6240 Phone: 747, 335, 7070

Phone: 717-235-7979 Fax: 717-235-8320

Adhesives Research Ireland Ltd. Raheen Business Park, Limerick, Ireland Phone: +353 61 300 300

Fax: +353 61 300 700

Adhesives Research Ltd. United Kingdom Phone: +44 (0)1371 878187

Adhesives Research Pte. Ltd.

20 Maxwell Road #10-06 Maxwell House Singapore 069113 Phone: +65 6777 9580 Fax: +65 6777 7261

Adhesives Research China Co., Ltd.

703B Xin Da Mansion #322 Xian Xia Road Shanghai 200335, China Phone: +86 21 6150 4358 Fax: +86 21 6278 5576